

TEST REPORT

No. : SM070401402

Date : Apr.12,2007

Page: 1 of 3

WENZHOU HAOSHI LIGHT INDUSTRIAL PRODUCTS CO., LTD
 NO.7 BEITOU INDUSTRIAL ZONE SHUANGAO SHUANGYU, WENZHOU 325000 ZHEJIANG CHINA
 TEL: 0086-577-88769586 FAX: 0086-577-88769585 WWW.SEALSEALS.COM

The following sample(s) was/ were submitted and identified on behalf of the client as:


Sample Name : HIGH SECURITY SEALS-CABLE SEAL HS028 WITH WIRE 4MM
 Sample Number : SM070401402
 SGS Ref. No. : SHD2703580
 Item No. : HS028
 Test Required : Tension test
 Ref. standard : ISO 17712-2006
 Date of Receipt : Apr.06,2007
 Test Period : Apr.06,2007 to Apr.12,2007

Test result(s) : (Please refer to the attached photos)

Test item	Test Method	Result	1#	2#
Tension test	SGS in-house method	MAX FORCE (kN)	11.60	11.91

***** To be continued *****

Signed for SGS-CSTC Standards
 Technical Services Co., Ltd



Robin Du
 Materials Lab Technical Supervisor


This Test Report is issued by the Company subject to its General Conditions of Service printed overleaf or attached. Said Conditions are also available upon request or are accessible at www.sgs.com. Attention is drawn to the limitations of liability, indemnification and jurisdictional policies defined therein. The results shown in this Test Report refer only to the sample(s) tested unless otherwise stated and such sample(s) are retained for 90 days only. This Test Report shall not be reproduced except in full, without written approval of the Company.

TEST REPORT


No. : SM070401402

Date : Apr.12,2007

Page: 2 of 3



Before test 1#



After test 1#

***** To be continued *****


This Test Report is issued by the Company subject to its General Conditions of Service printed overleaf or attached. Said Conditions are also available upon request or are accessible at www.sgs.com. Attention is drawn to the limitations of liability, indemnification and jurisdictional policies defined therein. The results shown in this Test Report refer only to the sample(s) tested unless otherwise stated and such sample(s) are retained for 90 days. This Test Report shall not be reproduced except in full, without written approval of the Company.

TEST REPORT


No. : SM070401402

Date : Apr.12,2007

Page: 3 of 3



Before test 2#



After test 2#

***** End of report *****

This Test Report is issued by the Company subject to its General Conditions of Service printed overleaf or attached. Said Conditions are also available upon request or are accessible at www.sgs.com. Attention is drawn to the limitations of liability, indemnification and jurisdictional policies defined therein. The results shown in this Test Report refer only to the sample(s) tested unless otherwise stated and such sample(s) are retained for 90 days. This Test Report shall not be reproduced except in full, without written approval of the Company.

